

Technical data sheet A41704 - granular

BÜHNEN GmbH & Co. KG
Hintern Sielhof 25
28277 Bremen · Germany

Telefon +49 (0)421 51 20 - 125
Telefon +49 (0)421 51 20 - 260
www.buehnen.de

HOT MELT

Part numbers: A41704 - granular

APPLICATORS:

HB 700-serie
HB Bulk Systems

APPLICATIONS

All-purpose hot melt, specially suitable for bonding of insulating materials and timber frames.

PROPERTIES

This hot melt is characterized by very good spraying properties and a medium open time. He shows very good adhesions on paper and cardboards, also on treated paper, metal and many plastics such as ABS, PS, PVC, PC, PET, PA and PMMA.

DESCRIPTION

Type : Hot melt adhesive based on ethylene vinyl acetate copolymer

Colour : Yellow

Composition : The components of this hot melt adhesive are classified as completely harmless. There is thus no need for special labelling of this product in compliance with German regulations for dangerous materials.

TECHNICAL DATA

Softening point : Approx. 95 °C Ring and ball

Heat resistance : Approx. 50 °C (WPS 68, shearload 100 g/cm²)

Viscosity : approx. 4500 mPas at 180 °C (Brookfield)

Specific gravity : approx. 0.97 g/cm³

Solids content : 100%

Working temperature : 160-180 °C

Open time : approx. 60 s, depending on material and quantity of adhesive applied (strip shaped application, dia. 3 mm, 180 °C , material strip (thickness 4 mm).

Setting time : approx. 45 s, depending on insulating effect of materials to be bonded and on application method and kind of material (see above open time).

Size : granular - loose charged

PACKAGING

granular - 25-kg-sack

Slight variation in the colour of the adhesive is normal and should not be seen as a quality problem.

STORAGE

Minimum two year shelf life under normal indoor conditions and when stored in the original packaging. Exposure to heat (direct sunlight) should be avoided at all costs to prevent possible damage, distortion or degradation of the adhesive.

APPLICATION

The surfaces to be bonded must be free of dust, dirt, moisture, grease, release agents. Attention: Plastic- and paint-materials containing plasticizers may destroy bond strength.

Apply adhesive as a spot, continuous strip or bead and join the parts together immediately. Short-time pressure will increase the bond strength.

SPECIAL NOTES

The safety and operating instructions for the applicator must be observed! Attention: Hot! The molten adhesive and the nozzle of the gun can reach temperatures which may cause skin burns if accidentally touched. In such cases submerge the affected area in cold water immediately. Do not try to remove the adhesive and seek proper medical attention.

Even when using the hot melt within the correct temperature range a slight fume is produced. If the working temperature is exceeded these fumes may result in the irritation of mucous-membranes in sensitive people. A preventive ventilation should exist.

With the vapor of the hot melt adhesive 1704 a slight quantity of acitic acid is released.

REMARKS

The details in our instruction sheets and other publications are provided to the best of our knowledge. Their contents are not, however, legally binding. In all cases, we recommend that preliminary tests are carried out by the customer. In all other respects, our General Terms of Sale apply.

Professional advice and rapid response from our central office in Bremen ensure you of reliable service.